

5F Annex Dragon Pearl Plaza
2123 Pudong Avenue
Shanghai 200135 - P.R. CHINA
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33
E-mail : ctcshanghai@ctcgroupe.com

Report No.: S190709422_1

02 August 2019

APPLICANT: TAICANG SHUNLIN太仓市顺林针织品有限公司
(C34448)
江苏太仓沙溪镇周泾路158号
· · ·
CHINA

Date of receipt : 29 July 2019
Testing period : 29 July 2019
: 02 Aug. 2019

Buyer: ---

Sample description: HPPE 防割护臂

Test(s) requested : ---
Service : REGULAR
Brand / Section : ---
Season : ---
End use : 防割护臂
Factory name : ---
Factory code : ---


For CE Marking : Yes
Previous report : ---
Product category : ---
Product type : ---
Test stage : FIRST TEST
Supplier name : ---
Exported to : ---

1. Conclusion:

	Tests description	Conformity
	EN 388	
1	Cut resistance : 2016	Level 4

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by



Henry YAN
Laboratory Manager



Report No.: S190709422_1

02 August 2019

APPLICANT: TAICANG SHUNLIN太仓市顺林针织品有限公司
(C34448)

2. Sample(s) description assigned by laboratory:

<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
	SLEEVE	Sleeve	



190709422

Report No.: S190709422_1

02 August 2019

APPLICANT: TAICANG SHUNLIN太倉市順林針織品有限公司
(C34448)

3. SLEEVE/

Sleeve

	Method	Client Requirement	Unit	Result	Conformity
(+) 4.1. Cut resistance : 2016	EN 388 : 2016				
Deviation from the test method				No	
used consumables - canvas				LEM 6	
used consumables - blade				OLFA RB45	
C1				1.3	
T1				60.0	
1C1				6.8	
I1				15.8	
C2				1.2	
T2				60.0	
1C2				7.4	
I2				15.0	
C3				1.2	
T3				60.0	
1C3				7.7	
I3				14.5	
C4				1.2	
T4				60.0	
1C4				7.3	
I4				15.1	
C5				1.2	
T5				60.0	
1C5				7.3	
I5				15.1	
Mean value of test piece 1				15.1	
C1 bis				1.2	
T1 bis				60.0	
2C1bis				6.3	
I1 bis				17.0	
C2 bis				1.2	
T2 bis				60.0	



Report No.: S190709422_1

02 August 2019

APPLICANT: TAICANG SHUNLIN太倉市順林針織品有限公司
(C34448)

	Method	Client Requirement	Unit	Result	Conformity
2C2bis				8.4	
I2 bis				13.5	
C3 bis				0.8	
T3 bis				60.0	
2C3bis				7.7	
I3 bis				15.1	
C4 bis				1.4	
T4 bis				60.0	
2C4bis				8.3	
I4 bis				13.4	
C5 bis				0.8	
T5 bis				60.0	
2C5bis				8.9	
I5 bis				13.4	
Mean value of test piece 2				14.5	
Considered value				14.5	
Performance level				4	
Observation				First sequence Cn+1 higher than 3xCn, switch to EN13997	

END OF TEST REPORT

(+)CNAS accreditation

Table of Performance Level for Glove

Test Item	Performance Level					
	0 ^{##}	1	2	3	4	5
Blade Cut Resistance (EN 388) Index (I) (minimum)	<1.2	1.2	2.5	5.0	10.0	20.0

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard