

5F Annex Dragon Pearl Plaza 2123 Pudong Avenue Shanghai 200135 - P.R. CHINA Tél.: +86 21 68 55 50 32

Fax: +86 21 68 55 50 33
E-mail: ctcshanghai@ctcgroupe.com

TEST REPORT

Page 1/3

Report No.: S170405004_1

21 April 2017

APPLICANT: 太仓市顺林针织品有限公司(C34448)

江苏太仓市沙溪镇周泾路158号

Date of receipt :19 Apr. 2017

Testing period :21 Apr. 2017

:21 Apr. 2017

Test(s) requested :— For CE Marking : Yes

Service :EXPRESS Previous report :
Brand / Section :-- Product category :
Season :-- Product type :-

End use :— Test stage :FIRST TEST

Factory name :— Supplier name :— Factory code :— Exported to :—

1. Conclusion:

Buyer: --

	<u>Tests description</u>	<u>Conformity</u>	
1	Abrasion resistance : 2016 : EN 388 : 2016	Level 1	
2	Tear strength resistance: 2016 : EN 388 : 2016	Level 3	

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by

Henry YAN
Laboratory Supervisor

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.



TEST REPORT

Page 2/3

Report No.: S170405004_1 21 April 2017

APPLICANT: 太仓市顺林针织品有限公司 (C34448)

2. Sample(s) description assigned by laboratory:

Size	Analyzed product	<u>Description</u>	Sample information
	GLOVE		
		palm	



170405004



TEST REPORT

Page 3/3

Report No.: S170405004_1

21 April 2017

APPLICANT: 太仓市顺林针织品有限公司(C34448)

3. GLOVE/

palm

	Method	Client Requirement	Unit	Result	Conformity
Tear strength resistance: 2016	EN 388 : 2016	Requirement			
Tear strength			N	63	
Tear strength (2)			N	66	
Tear strength (3)			N	>75	
Tear strength (4)			N	>75	
Performance level				3	
Abrasion resistance : 2016	EN 388 : 2016				
Deviation from the test method				NO	
used consumables - abrasive				Klingspor PL31B Grit 180	
used consumables - adhesive				3M	
Number of cycles at the hole detection				200	
Number of cycles at the hole detection (2)				100	
Number of cycles at the hole detection (3)				100	
Number of cycles at the hole detection (4)				200	
Performance level				1	

END OF TEST REPORT

Table of Performance Level for Glove

Test Item	Performance Level					
1001110111	0##	1	2	3	4	5
Abrasion Resistance (EN 388) Number of cycles (minimum)	<100	100	500	2000	8000	
Tear Resistance (EN 388) Force (N) (minimum)	<10	10	25	50	75	

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard